

**TEST REPORT**

**Client:** Gabriel  
Hjulgagervej 55  
Postbox 59  
DK-9100 Aalborg  
Denmark

**Entry No:** 103855-01

**Date received:** 11/12/2018

**Client's Description:** Xpress, 2,9mm Foam

**Test Required:** Abrasion

**Conditioning:** In accordance with BS EN ISO 139: 2005 for a minimum of 24 hours at 65+/-4%, Relative Humidity, 20+/-2°C

**Date Tests Completed:** 29/01/2019

**Abrasion Resistance:** BS EN ISO 12947-2: 2016<sup>F</sup>

The tests were carried out using a pressure of 12 +/- 0.3 kPa

The criterion for judging end point was three threads broken.

Specimen 1	40,000 rubs
Specimen 2	40,000 rubs
Specimen 3	50,000 rubs
Specimen 4	50,000 rubs
<b>Overall Result</b>	<b>40,000 rubs</b>

Change in colour after 6,000 rubs: **4-5**

Observation Technique: 10 fold magnification  
Type of Fabric: Flat Woven

-----End of Document-----

*This is hereby certified to be a correct return of the tests made of the items referred to herein*

❖ Unless stated otherwise, all tests are carried out in accordance with the current edition of the relevant standard.  
❖ Test results are valid for a period of 12 months from the date of issue of this certificate.  
❖ Tests marked <sup>S</sup> in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.  
❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.  
❖ Uncertainty budgets for test methods contained within this report are available on request.  
This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

sed of after 28 days.  
ation Schedule for this Laboratory.  
Flexible Scope of Accreditation.



1104