



Textilní zkušební ústav, s.p.
TESTING LABORATORY
Cejl 480/12, 602 00 Brno, Czech Republic

TESTING LABORATORY 1001

accredited according to ČSN EN ISO/IEC 17025:2018 by the Czech Accreditation Institute

TEST REPORT

AZL 24/0703-01

CUSTOMER: Nord Fabric JSC
J. Dobkevičiaus g. 8a
021 89 Vilnius
Lithuania

SAMPLE: Fabric RIPSTOP HW
(according to the customer order) Fibre composition: 50 % polyamide, 47 % cotton, 3 % elastane
Colour: dark blue



Textilní zkušební ústav
Cejl 480/12
602 00 Brno



The laboratory is not responsible for information supplied by the customer that may affect the validity of test results.

CONDITIONS OF APPLICATION OF THE TEST REPORT:

Test Report contains results of the tests related to the submitted sample only. Sampling has been done by the customer. The Report may not be reproduced in any way other than as a complete set. Reproduction of certain parts of the Report is subject to approval of the test laboratory, which has issued it. All information about subcontracted tests results or unaccredited test methods is presented in text part of the test report. Unless otherwise stated, all tests were performed at the address, listed in the header.

PREPARED BY: P. Klopárová
CHECKED BY: A. Uhrová
NUMBER OF PAGES: 2

DATE OF ACCEPTANCE:
12.06.2024

DATE OF EXAMINATION:
13.06.2024

DATE OF ISSUE:
18.06.2024



+420 543 426 730
www.tzu.cz
azl@tzu.cz



Textilní zkušební ústav, s.p.

Determination of hydrocarbon resistance (oil repellency)

was tested according to ČSN EN ISO 14419:2010 - Hydrocarbon resistance test

- conditions of testing: ČSN EN ISO 139:2005; temperature (20±2) °C; RH (65±4) %
- specimens tested: 3
- testing area: ca 20 x 20 cm

Treatment before testing:

- no treatment, tested in original state

	Results – original material
RIPSTOP HW	6 (n-decane)

Result: oleophobicity degree – numerical rating corresponding to the highest-numbered test liquid, which does not wet the tested substrate within period (30±2) s

Approved by:

Markéta Hrubanová
Head of Testing Laboratories

End of report

