

**CERTIFICATE No. 564****POLYURETHANE FOAM****REFERENCE NUMBER: IST 5370365-02**

- | | | |
|----|--------------------|-------------------|
| 1. | Trade-mark of PPU | VB 2540 |
| 2. | Date of production | 05.03.2024 |
| 3. | Batch No. | 0564 |

No	Foam properties	Measure unit	Requirements	Proof method	Result
1.	Colour	According to IST	-	visually	White
2.	Rel. density (net)	kg/m ³	23,75 - 27,50	ISO 845	25,3
3.	Compression set: (50% 70°C 22h), max.	%	6	ISO 1856	3,1
4.	Tensile strength, min. Elongation at break, min	kPa %	80 120	ISO 1798	
5.	Resilience, min.	%	37	ISO 8307	37
6.	Hardness, (ILD, 40%)	N	123,00 - 177,00	ISO 2439	156,5
7.	SAG factor	-	≥ 1,9	ISO 2439	2,5
8.	Flammability				

CONCLUSION: ☒ **Complies with the requirements**☐ **Does not comply****Remark:**

G.Cicėnienė
Quality manager

R.Podlipskienė
Tested by

