


Client

Date sample received: 2010-12-16

Date test performed: 2010-12-20 - 2011-01-03

Sample description: **Tests conducted - Results**

(A)=Accredited method

(A) Resistance to abrasion, Martindale 105000, 105000, 110000 mean: 106700
(SS-EN ISO 12947-2:1999), 12 kPa,
2 threads broken, Conditioned and
performed in 20±2°C, 65±4 % RH.
No.of rubs

2011-01-07 

Technical manager

Responsible technical assistant

The test results relate only to the stated items.

Testing laboratories are accredited by the Swedish Board for Accreditation and Conformity Assessment (SWEDAC) under the terms of Swedish legislation. The accredited laboratory activities meet the requirements in SS-EN ISO/IEC 17 025 (2005).

This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

**The Textile & Leather Laboratory Stockholm AB**

PB 4707, SE-116 92 Stockholm

Visitors, Alsnögatan 7

Phone +46 8 615 83 80, Fax +46 8 644 77 60

e-mail: info@textillab.se