

Number: [REDACTED]

Date: Jul 31, 2023

Applicant: U GROUP SRL  
VIA BORGOMANERO,  
50-28040 PARUZZARO( NO ) - ITALY

Attn: SINDY

Sample Description:

Three (3) groups of submitted samples said to be:

(A) One (1) piece of BLACK CARBON fleece 100% POLYESTER 280G

(B) One (1) piece of GREY METEORITE fleece 100% POLYESTER 280G

(C) One (1) piece of DEEP BLUE fleece 100% POLYESTER 280G.

Test Method : BS EN ISO 12947-2:2016 / ISO 13938-2:1999/ ISO 12945-1:2020

Style No./Name : FLEECE 100% polyester, polar fleece 280 g/m<sup>2</sup>, brushed both side.

Background Fabric : --

Country Of Origin : MADE IN CHINA

Date Received/Date Test Started : July 07, 2023

Date Final Information Confirmed: July 28, 2023

---

Test Result Please Refer To Attached Page(S).

---

Should you have any query on this report, you may contact at [gzfootwear@intertek.com](mailto:gzfootwear@intertek.com)

Authorized By:  
For Intertek Testing Services Shenzhen Ltd.  
Guangzhou Branch

[REDACTED]  
Guiliang Dong  
Senior Lab Manager

wx/lydiayang



**Intertek Testing Services Shenzhen Ltd. Guangzhou Branch**  
深圳天祥质量技术服务有限公司广州分公司  
Room 401/501/601/801/901/1003, No. 8, East BaoYing Road, Huangpu District, Guangzhou 510730  
广州市黄埔区保盈东路8号401房、501房、601房、801房、901房、1003房  
Tel: +86 020 28209114 Postcode: 510730

[www.intertek.com](http://www.intertek.com)

检验检测专用章

SHENZHEN BRANCH (6)

- Martindale Abrasion (BS EN ISO 12947-2:2016, Nominal Pressure: 9 kPa; Condition In  $20 \pm 2^\circ\text{C}$ ,  $65 \pm 5\% \text{R.H}$  For 18 Hours And Tested In This Atmosphere)

(A)

After 2,000 Revs:

Observation:

Slight Wear

- Bursting Strength Of Knitted Materials (ISO 13938-2:1999)

Test Condition:

Machine: Pneumatic Type Bursting Tester

Diaphragm Diameter: 79.8 mm

Test Area: 50 cm<sup>2</sup>

Sample	Result
(A)	Over 100.0 kPa

- Fabric Propensity to Surface Pilling, Fuzzing or Matting (ISO 12945-1:2020, Pilling Box Method):

**As Received**

(A)			
Mean Grade			
Hours	Pilling	Fuzzing	Matting
5H	3-4	3-4	3-4


**After 5 Cycles Washing**

(A)			
Mean Grade			
Hours	Pilling	Fuzzing	Matting
5H	3-4	3-4	3-4

Remark:

The visual assessment of pilling, fuzzing and matting was carried out respectively according to ISO 12945-4.

This Test Was Conducted At Room 801/901, No. 8, East BaoYing Road, Huangpu District, Guangzhou.



End of Report

*This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. No copy of the test report(except for full text copy) shall be made without the written approval by Intertek.*