

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton  
 Lancashire : BL4 8NB  
 Tel: +44 (0) 1204 792858  
 Email: enquiries@ltslab.co.uk  
 www.ltslab.co.uk



9630

**TEST CERTIFICATE**

<b>CLIENT:</b>	Camira Fabrics Meltham Mills, Meltham Huddersfield HD9 4AY - -	<b>Certificate Number:</b>	<b>UK2001109 -1</b>
		<b>Date Received:</b>	03/12/2020
		<b>Date Issued:</b>	07/12/2020
		<b>Issue Number:</b>	1
<b>Contact:</b>	Rebecca Grimes	Changes from previous issue (if applicable)	
<b>Tel:</b>	01924 481366		
<b>Email:</b>	rebecca.grimes@camirafabrics.com		

**SAMPLE IDENTIFICATION**

The information in this section is provided by the client and Lancashire Testing Services Ltd assumes no responsibility or liability for its accuracy.

Sample Name / Reference	Rivet
Additional Names:	-
Batch Ref/Number:	435510
Order Number:	9719
Colour:	HECL18
Fabric Composition:	100% Repreve Recycled Polyester
Customer:	-

**SPECIFICATION**

BS7176:2007 + A1:2011 - Low Hazard

**TEST METHOD**

Flammability:	BS EN 1021-1:2006 Part 1: Ignition source smouldering cigarette BS EN 1021-2:2006 Part 2: Ignition source match flame equivalent
Pre-treatment:	None Requested

**Conclusion**

The sample tested: **Complies** with the flammability requirements of:  
BS 7176:2007 + A1:2011 Low hazard, taking into account uncertainty of measurement.

Uncertainty of Measurement: ±1 second - timing measurements, ±1mm - dimensional measurements

**Comments:**

Please note that copies of this original certificate are not valid

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality



**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton  
 Lancashire : BL4 8NB  
 Tel: +44 (0) 1204 792858  
 Email: enquiries@ltslab.co.uk  
 www.ltslab.co.uk



9630

**TEST CERTIFICATE**

**Test Results:-**  
**BS7176:2007 + A1:2011 - Low Hazard - Specification for resistance to ignition of upholstered furniture for non-domestic seating by testing composites**

*"The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use."*

Sample Code		UK2001109 -1				
Sample Name / Reference		Rivet				
Client		Camira Fabrics				
Date of test		07/12/2020				
Pre-Treatment		None Requested -				
Filling Type		Carpenter/RX36110 CMHR polyurethane foam of approximate density 36Kg/m3				
Size of test rig		Small: Back - 450 x 300 ± 2mm + Seat - 450 x 150 ± 2mm				
Test Conditions		Period h	Temperature °C	Relative humidity %	Air Flow m/s	Volume m <sup>3</sup>
Conditioning of test specimens		≥24	23±2	50±5	-	-
Testing conditions		-	10-30	15-80	0.02-0.2	≥6
Testing Source		Smouldering Cigarette Source				
Testing time limit		60 minutes after placement of smouldering cigarette.				
Test No.	Position	Ignition/N on Ignition	Duration of: (min.sec)			Smouldering and flaming criteria exceeded: (If any)
			Ignition Source	Flames	Smoke	
1	LHS	NI	16.43	-	19.25	-
2	M	NI	16.17	-	18.14	-
2	-	-	-	-	-	-
Testing Source		Match flame equivalent				
Testing time limit		2 minutes after removal of burner tube (120 seconds)				
Test No.	Position	Ignition/N on Ignition	Duration of: (sec)			Smouldering and flaming criteria exceeded: (If any)
			Ignition Source	Flames	Smoke	
1	LHS	NI	15	15	24	-
2	M	NI	15	15	26	-
3	RHS	NI	15	15	27	-
<b>RESULT:</b>		<b>SMOULDERING CIGARETTE SOURCE</b>				<b>PASS</b>
		<b>MATCH FLAME EQUIVALENT</b>				<b>PASS</b>
KEY: I = Ignition, NI = Non Ignition, LHS = Left hand side, M = Middle, RHS = Right hand side						

On behalf of Lancashire Testing Services :

 <div style="border: 1px solid red; width: 100px; height: 30px; margin: 5px auto;"></div> Tony Alcock, Laboratory Technician:	John Marsh, Laboratory Technician:	 <div style="border: 1px solid red; width: 100px; height: 30px; margin: 5px auto;"></div> Peter Collings, Operations Manager:
---	---------------------------------------	---

**Issue Number: 1**

Please note that copies of this original certificate are not valid

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

[www.ltslab.co.uk](http://www.ltslab.co.uk)

9630

**TEST CERTIFICATE****Certificate Number: UK2001109-1**

If the measurement result plus/minus the expanded uncertainty with a 95 % coverage probability overlaps the limit, it is not possible to state compliance or non-compliance. The measurement result and the expanded uncertainty with a 95 % coverage probability will then be reported. The report will include the actual value with the uncertainty range.

Lancashire Testing Services Ltd have conducted thorough analysis of the uncertainty of all measurements carried out in the application of the standard or standards detailed in this report. Where possible any associated uncertainty of measurements have been accounted for in the working instructions, so that they have no impact on the reporting of the final result. In instances where uncertainty of measurements can only be taken into account after the test has been conducted, these uncertainty values have been stated on this report. The stated uncertainty of measurement has also been taken into account in the final reporting of the overall result.

**Issue Number: 1**

Please note that copies of this original certificate are not valid

This report relates only to the sample tested and does not guarantee the bulk of the material to be of equal quality



**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: [enquiries@ltslab.co.uk](mailto:enquiries@ltslab.co.uk)

[www.ltslab.co.uk](http://www.ltslab.co.uk)



9630



**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: [enquiries@ltslab.co.uk](mailto:enquiries@ltslab.co.uk)

[www.ltslab.co.uk](http://www.ltslab.co.uk)



9630