

# SURGICRYL<sup>®</sup>

## RAPID

### POLYGLYCOLIC ACID

1.3. Sintetiniai, pinti, trumpos rezorbcijos chirurginiai siūlai, sudėti: polikaprolaktonas ir kalčio steratas (1%). Pilna rezorbcija per 42 d. Procentinis stiprumo išlaikymas - 50% po 5 -7 dienų.

<b>Type</b>	Braided and coated multifilament
<b>Composition</b>	Polyglycolic acid
<b>Coating</b>	Polycaprolactone and calcium stearate (1%)
<b>Colour</b>	Beige - undyed / Violet
<b>Tissue reaction</b>	Minimal
<b>Absorption</b>	The hydrolytic action by which the material is broken down results in total absorption in approximately 42 days. Approximately 50% of tensile strength remain after 7 days.
<b>Presentation</b>	Box with 12 sutures

Adatos tvirtos, nelūžta ir nesilanksto, pagamintos iš ne prastesnio nei 300 AISI serijos nerūdijančio plieno. Supakuoti po vieną, sterilioje pakuotėje



For quality  
&  
safety

[www.sutures.be](http://www.sutures.be)