



TEST REPORT

Client: Gabriel
 Hjulmagervej 55
 Postbox 59
 DK-9100 Aalborg
 Denmark

Entry No: 96488

Date received: 13/03/2018

Client's Description: Sample of fabric: Cura, Colour: 65104

Test Required: Abrasion and Pilling in accordance with BS EN 14465

Conditioning: In accordance with BS EN ISO 139: 2005 for a minimum of 24 hours at 65+/-4%, Relative Humidity, 20+/-2°C

Date Tests Completed: 10/04/2018

Abrasion Resistance: BS EN ISO 12947-2: 2016^F

The tests were carried out using a pressure of 12 +/- 0.3 kPa
 The criterion for judging end point was three threads broken

Specimen 1	180,000 rubs
Specimen 2	170,000 rubs
Specimen 3	160,000 rubs
Specimen 4	170,000 rubs
Overall Result	160,000 rubs

Change in colour after 6,000 rubs: **4-5**

Observation Technique: 10 fold magnification
 Type of Fabric: Flat Woven

Pilling: BS EN ISO 12945-2: 2000 Load 415g

	<u>Rating</u>
After 2,000 rubs	5
After 5,000 rubs	4-5

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein

Vivienne Brockbank
 Technician
 10 April 2018

- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
 - ❖ Tests marked ^N in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
 - ❖ Tests marked ^F in this certificate are performed under the Laboratory's Flexible Scope of Accreditation.
 - ❖ Tests marked ^S in this certificate have been subcontracted to another ISO17025 Accredited Laboratory.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ Uncertainty budgets for test methods contained within this report are available on request.
- This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



1104



BANDYMŲ ATASKAITA

Klientas: Gabriel
Hjulumagervej 55
Postbox 59
DK-9100 Aalborg
Danija

Įrašo Nr.: 96488

Gavimo data: 2018-03-13

Kliento aprašymas: Audinio pavyzdys: Cura, spalva: 65104

Reikalingas bandymas: Dilimas ir skilimas pagal BS EN 14465

Kondicionavimas: Pagal BS EN ISO 139: 2005 mažiausiai 24 valandas esant 65+/-4 %, santykinei oro drėgmei, 20+/-2 °C

Bandymų užbaigimo data: 2018-10-04

Atsparumas dilimui: BS EN ISO 12947-2: 2016^F

Bandymai buvo atlikti naudojant 12 +/- 0,3 kPa slėgį
Galutinis taško vertinimo kriterijus buvo trys nutrūkę siūlai

1 mėginys	180,000 patrynimų
2 mėginys	170,000 patrynimų
3 mėginys	160,000 patrynimų
4 mėginys	170,000 patrynimų
Bendras rezultatas	160,000 patrynimų

Spalvos pasikeitimas po 6000 patrynimų: **4–5**

Stebėjimo technika: 10 kartų padidinimas
Audinio tipas: Plokščias austas

Pumpuravimasis: BS EN ISO 12945-2: 2000, 415 g apkrova

	Įvertinimas
Po 2000 patrynimų	5
Po 5000 patrynimų	4–5

-----Dokumento pabaiga-----

Patvirtinama, kad šiame dokumente pateikti teisingi nurodytų elementų bandymų rezultatai.

/parašas Vivienne Brockbank
Technikas
2018 m. balandžio 10 d.

- ❖ Jei klientas nenurodė kitaip, mėginio likučiai bus sunaikinti po 28 dienų.
 - ❖ Bandymai, pažymėti N šiame sertifikate, neįtraukti į UKAS akreditavimo šiai laboratorijai planą.
 - ❖ Bandymai, pažymėti F šiame sertifikate, atliekami pagal laboratorijos lanksčią akreditavimo sritį.
 - ❖ Bandymai, pažymėti S šiame sertifikate, buvo perduoti kitai ISO17025 akredituotai laboratorijai.
 - ❖ Šiame dokumente išreikštos nuomonės ir interpretacijos nepatenka į UKAS akreditavimo sritį.
 - ❖ Paprašius galima gauti šioje ataskaitoje pateiktų bandymų metodų neapibrėžtumus.
- Šis sertifikatas yra susijęs tik su gautu mėginiu ir, jei to mėginio nepaėmė šios laboratorijos darbuotojai arba jos atstovai ir jo atitinkamai nepatvirtino, už bet kokią rezultato pritaikymą dideliame kiekiu ar kitai medžiagai yra atsakingas klientas.





VERTIMO SERTIFIKATAS

SERTIFIKATO NR. 15513

2024-01-26

Mes, „Vertimų karaliai“ UAB, įmonės kodas 304255745, patvirtiname, kad atliktas vertimas yra tikslus ir atitinka vertimui pateiktą originalą. Vertimą atliko mūsų vertėjas profesionalas, kuris dirba mūsų įmonėje pagal darbo sutartį Nr. 1 ir yra kompetetingas versti toliau nurodytą kalbų kombinaciją.

Vertimas iš:

Vertėjas:

Tel. numeris:

Adresas:



Parašas

Autentiškumo patikrinimui

